



Cerafelt products are lightweight, flexible refractory fiber insulators formed from exceptionally pure refractory oxides and bonded with an organic binder.

These products are recommended for a wide range of high-temperature industrial applications such as expansion joints in kilns, furnaces, and boiler walls, and high-temperature gaskets.

When used as a gasket, Cerafelt exhibits excellent resistance to penetration from molten metals, both ferrous and nonferrous. This unique property, coupled with its ease of fabrication, makes it ideal for ingot stool seals, stopper rod gaskets, and gaskets for aluminum billet casting.

Features

- Lightweight and flexible
- Low thermal conductivity and heat storage

Applications

- Expansion joints
- Gaskets
- Molten metal resistant insulation

Standard Sizes

Thickness, in (mm)	Density, pcf (kg/m ³)	4 (64)	6 (96)	8 (128)	10 (160)	12 (192)	24 (385)
Cerafelt							
1/8 (3.125)	—	—	—	—	—	X	X
1/4 (6.25)	—	X	X	X	—	X	X
1/2 (12.5)	X	X	X	X	X	X	X
3/4 (18.75)	—	—	—	X	X	X	—
1 (25)	X	X	X	X	X	X	—
1 1/2 (37.5)	X	—	—	—	—	—	—
2 (50)	X	—	—	—	—	—	—

Cerachrome Felt

	6 (96)	8 (128)	12 (192)	24 (385)
1/4 (6.25)	—	—	X	X
1/2 (12.5)	X	X	X	X
1 (25)	X	X	—	—

Standard Dimensions: 96 in. x 48 in. sheets.

Cerafelt Cerachrome Felt

Product Information

Physical Properties

	Cerafelt	Cerachrome Felt
Color	cream/tan	blue/green
Density, compressed, pcf (<i>kg/m³</i>)	4, 6, 8, 10, 12, 18, 24 (64, 96, 128, 160, 192, 288, 385)	6, 8, 12, 24 (96, 128, 160, 385)
Thickness, in. (<i>mm</i>)	1/8 - 1 (3.125 - 25)	1/4 - 1 (6.25 - 25)
Max. Temperature Rating, °F (°C)	2300 (1260)	2600 (1427)

Chemical Analysis, nominal % weight basis after firing

Alumina, Al ₂ O ₃	46	43
Silica, SiO ₂	54	54
Chromium oxide, Cr ₂ O ₃	—	3
Loss on ignition, L.O.I.	3 - 9	3 - 9
Other	trace	trace

Thermal Conductivity, BTUin./hrft²F (w/mk)

Mean temperature	8 pcf	8 pcf
500°F (260°C)	0.46 (0.07)	0.43 (0.06)
1000°F (538°C)	0.94 (0.14)	0.87 (0.13)
1500°F (816°C)	1.58 (0.23)	1.49 (0.21)
2000°F (1093°C)	2.29 (0.33)	2.18 (0.31)

Airflow Resistance, (cfm/in. w.c./ft²/in.)

Temperature, °F (°C)	Density, pcf (<i>kg/m³</i>)							
	<u>4 (64)</u>	<u>6 (96)</u>	<u>8 (128)</u>	<u>10 (160)</u>	<u>12 (192)</u>	<u>14 (224)</u>	<u>18 (288)</u>	<u>24 (385)</u>
75 (24)	64.4	31.1	18.9	12.8	8.9	6.7	4.3	2.6
1000 (538)	32.2	15.6	9.4	6.4	4.4	3.3	2.2	1.6
2000 (1093)	23.6	11.2	6.8	4.3	3.2	2.4	1.3	0.9

Sound Absorption Coefficients, No. 4 Mounting, 8 pcf (128 kg/m³)

Thickness, in. (<i>mm</i>)	Cycles Per Second							NRC*
	125	250	500	1000	2000	4000		
1/2 (12.5)	07	12	45	72	77	85	50	
1	21	69	86	84	86	99	80	
2	92	78	81	83	81	79	80	
3	65	80	83	88	85	83	85	

* Noise Reduction Coefficient – The average of the sound absorption coefficients at frequencies of 250, 500, 1000 and 2000 cycles per second.

The values given herein are typical average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Therefore, the data contained herein should not be used for specification purposes. Check with your Thermal Ceramics office to obtain current information.

Thermal Ceramics is a trademark of The Morgan Crucible Company plc. Cerafelt and Cerachrome are trademarks of Thermal Ceramics Inc.

Marketing Communications Offices

Thermal Ceramics Americas

T: (706) 796 4200

F: (706) 796 4398

Thermal Ceramics Asia Pacific

T: +65 6733 6068

F: +65 6733 3498

Thermal Ceramics Europe

T: +44 (0) 151 334 4030

F: +44 (0) 151 334 1684

North America - Sales Offices

Canada

T: +1 (905) 335 3414

F: +1 (905) 335 5145

Mexico

T: +52 (555) 576 6622

F: +52 (555) 576 3060

United States of America

Eastern Region

T: +1 (800) 338 9284

F: +1 (866) 785 2764

Western Region

T: +1 (866) 785 2738

F: +1 (866) 785 2760

South America - Sales Offices

Argentina

T: +54 (11) 4373 4439

F: +54 (11) 4372 3331

Brazil

T: +55 (21) 2418 1366

F: +55 (21) 2418 1205

Chile

T: +56 (2) 854 1064

F: +56 (2) 854 1952

Colombia

T: +57 (2) 2282935/2282803/2282799

F: +57 (2) 2282935/2282803/23722085

Guatemala

T: +50 (2) 4733 295/6

F: +50 (2) 4730 601

Venezuela

T: +58 (241) 878 3164

F: +58 (241) 878 6712