

Range-Glas® XG™

Formaldehyde-free™ Thermal Insulation

Description

Range-Glas XG is a lightweight, Formaldehyde-free™ white insulation designed to provide excellent thermal performance in all types of residential and commercial ovens operating at temperatures up to 1000°F (538°C). The insulation blanket is manufactured from rotary—process fiber glass bonded with a special thermosetting acrylic resin.

Range-Glas XG insulation emits minimal smoke and odor during initial heat-up, the cleaning cycle of self-cleaning ranges or the initial broil cycle on standard ovens. This material performs equally well on continuous cleaning, standard and industrial ovens.

Range-Glas XG is available in roll form in a broad range of thicknesses, densities and dimensions. The friendlier feel of the blanket provides ease of handling during processing and installation.

Custom Fabrication

The Johns Manville nationwide network of Approved Fabricators specializes in secondary processing to supply custom parts to meet specific customer requirements. Die-cutting, laminating, special packaging and just-in-time delivery are just a few of the multiple capabilities our fabricators can provide.

Applications

- · Thermal insulation for residential ranges and ovens
- Thermal insulation for commercial ovens
- Thermal insulation for industrial ovens

Specifications

Temperature Limit: 1000°F (538°C)

Corrosiveness: Range-Glas XG passes ASTM C 665 for steel, aluminum and copper.

Fire Hazard Classification: Range-Glas XG meets 25/50 (per ASTM E 84 and UL 723 and CAN/ULC S102 - M88). Labels supplied when requested on order. Meets NFPA 90A and 90B.



Range-Glas XG - Available Densities/Thicknesses

Density		Thickness (in ½" [13 mm] Increments)		
pcf	kg/m³	in	mm	
1.02	16	1.0 - 4.0	25-102	
1.26	20	1.0 - 3.0	25-76	
1.76	28	1.0 - 2.0	25-51	
2.00	32	1.0 - 2.0	25-51	
2.50	40	1.0 - 1.5	25-38	

Sound Absorption Coefficients (Type "A" Mounting) for 1" (25 mm) Thickness

Density	/		
pcf	kg/m³	NRC	
1.02	16	0.65	
1.26	20	0.75	
1.76	28	0.80	
2.00	32	0.80	
2.50	40	0.80	

Note: Coefficients were tested in accordance with ASTM C 423 and ASTM E 795 test methods.

Range-Glas XG - Thermal Conductivity (k) Per ASTM C 518

	Thermal Conductivity (k)							
1	75°F (24°C) Mean Temperature		300°F (149°C) Mean Temperature		500°F (260°C) Mean Temperature			
kg/m³	Btu•in/(hr•ft²•°F)	W/m•°C	Btu•in/(hr•ft²•°F)	W/m•°C	Btu•in/(hr•ft²•°F)	W/m•°C		
16	0.26	0.037	0.46	0.066	0.74	0.107		
20	0.24	0.035	0.42	0.061	0.66	0.095		
28	0.23	0.033	0.38	0.055	0.58	0.084		
32	0.22	0.032	0.33	0.048	0.53	0.076		
40	0.22	0.032	0.33	0.048	0.48	0.069		
	kg/m³ 16 20 28 32	75°F (24°C) Mean Ruein/(hreft²e°F) 16 0.26 20 0.24 28 0.23 32 0.22	75°F (24°C) Mean Temperature Rtu•in/(hr•ft²•°F) W/m•°C 16 0.26 0.037 20 0.24 0.035 28 0.23 0.033 32 0.22 0.032	kg/m³ 75°F (24°C) Mean Temperature Btu•in/(hr•ft²•°F) W/m•°C 300°F (149°C) Mean Btu•in/(hr•ft²•°F) 16 0.26 0.037 0.46 20 0.24 0.035 0.42 28 0.23 0.033 0.38 32 0.22 0.032 0.33	kg/m³ 75°F (24°C) Mean Temperature Btu•in/(hr•ft²•°F) W/m•°C 300°F (149°C) Mean Temperature Btu•in/(hr•ft²•°F) W/m•°C 16 0.26 0.037 0.46 0.066 20 0.24 0.035 0.42 0.061 28 0.23 0.033 0.38 0.055 32 0.22 0.032 0.33 0.048	kg/m³ 75°F (24°C) Mean Temperature 300°F (149°C) Mean Temperature 500°F (260°C) Mean Temperature Btu•in/(hr•ft²•°F) W/m•°C Btu•in/(hr•ft²•°F) W/m•°C Btu•in/(hr•ft²•°F) 16 0.26 0.037 0.46 0.066 0.74 20 0.24 0.035 0.42 0.061 0.66 28 0.23 0.033 0.38 0.055 0.58 32 0.22 0.032 0.33 0.048 0.53		

Range-Glas® XG™

Formaldehyde-free™ Thermal Insulation

Insulation Systems, OEM Insulations

For Order Placement

 Eastern Region
 Western Region

 (Defiance, OH)
 (Littleton, CO)

 P.O. Box 158
 P.O. Box 625005

 Defiance, OH 43512
 Littleton, CO 80162

 (800) 426-2435
 (800) 293-3393

 Fax: (800) 329-7397
 Fax: (800) 741-0183

For Technical Information

(800) 458-7198



Insulation Systems

P.O. Box 5108
Denver, CO 80217-5108
Product Information: (800) 654-3103
pic@jm.com
www.jm.com

The physical and chemical properties of Range-Glas® XG™ Insulation listed herein represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Numerical flame spread and smoke developed ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions. Check with the Regional Sales Office nearest you to assure current information. All Johns Manville products are sold subject to Johns Manville's standard Terms and Conditions including Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville standard Terms and Conditions, Limited Warranty and Limitation of remedy, and information on other Johns Manville thermal insulations and systems, call (800) 654-3103.

