

Technical Product Information

RockBoard 35

BOARD INSULATION 07210* BOARD INSULATION 07 21 13** ACOUSTIC BOARD INSULATION 09 81 13** PROCESS EQUIPMENT INSULATION 40 42 23**

General Product Information:

ROXUL® products are mineral wool fibre insulations made from basalt rock and slag. This combination results in a noncombustible product with a melting point of approximately 2150°F (1177°C), which gives it excellent fire resistance properties. ROXUL mineral wool is a water repellent yet vapour permeable material.


Description & Common Applications:

The RockBoard[™]35 product is a semi-rigid mineral wool insulation board that is non-combustible, lightweight, water repellent, fire resistant and sound absorbent. This product is a general all purpose board with low thermal conductivity. This board can also be fabricated to different dimensions while still retaining fire, water and thermal properties.

Compliance and Performance:ASTM C 612Mineral Fiber Block and Board Thermal InsulationType IVA, Complies								
Fire Performance: ASTM E 136 CAN4 S114 ASTM E 84(UL 723) CAN/ULC S102	Behaviour of Materials at 750°C (1382°F) Test for Non-Combustibility Surface Burning Characteristics Surface Burning Characteristics	Non-Combustible Non-Combustible Flame Spread = 5 Smoke Developed = 5 Flame Spread = 5 Smoke Developed = 10						
Maximum Service Te ASTM C 411	mperature: Hot Surface Performance	In Compliance with ASTM C612 @ 1200°F(650°C)						
Dimensional Stability ASTM C 356	: Linear Shrinkage	0.35% @ 1200°F (650°C)						
Moisture Resistance: ASTM C 1104	Moisture Sorption	0.3%						
Fungi Resistance ASTM C1338	Determination of Fungi Resistance	Passed						
Thermal Resistance: ASTM C 518 (C 177)	R-value/inch @ 75°F RSI value/25.4 mm @ 24°C	4.1 hr.ft².F/Btu 0.72 m²K/W						
Corrosive Resistance ASTM C 665 ASTM C 795 ****	Corrosiveness to Steel Stainless Steel Stress Corrosion Specification as per Test Methods C871 and C692: U.S. Nuclear Regulatory Commision, Reg. Guide #1.36: U.S. Military Specifications MIL-I-24244 (all							

versions including B and C)

Thermal Conductivity (k):



Acoustical Performance

ASTM C423 CO-EFFICIENTS AT FREQUENCIES							
Thickness	125 Hz	250 Hz	500 Hz	1000 Hz	2000 Hz	4000 Hz	NRC
1.0"	0.08	0.23	0.66	0.93	1.02	1.02	0.71
1.5"	0.15	0.47	0.98	1.06	1.02	1.02	0.90
2.0"	0.26	0.68	1.14	1.13	1.06	1.07	1.00
3.0"	0.62	1.03	1.20	1.10	1.08	1.10	1.10
4.0"	1.07	1.01	1.07	1.06	1.07	1.06	1.05

Compressive Strength:

ASTM C 165	at 10%	71 psf (3.4 kPa)
	at 25%	209 psf (10 kPa)

Density:

ASTM C 612-00 – Actual 3.5 lbs/ft³ 56 kg/m³

Dimensions:

24" (width) x 48" (length) 610 mm (width) x 1219 mm (length)

36" (width) x 48" (length) 914 mm (width) x 1219 mm (length)

Thickness:

Product thickness is available in 1" to 4" in ½" increments.

Key Application Qualifiers:

- Easily cut
- Non-combustibleExcellent sound absorbency
- Excellent sound absort
- Chemically inert
- Does not rot or sustain vermin
 Does not promote growth of fungi or mildew
- Low moisture sorption
- Water resistant
- Water resistant
- CFC and HCFC free product and process
- Made from natural & recycled materials

Other ROXUL Products:

Please consult ROXUL for all your insulation needs. We have an extensive range of products for all applications from pipe insulation to commercial products to residential batts. ROXUL invites all inquiries and will act promptly to service all of your requirements.

*** "Provisions for lot testing may be required, consult manufacturer."

Note:

As ROXUL Inc. has no control over installation design and workmanship, accessory materials or application conditions, ROXUL Inc. does not warranty the performance or results of any installation containing ROXUL Inc's. products. ROXUL Inc's. overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty is in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose.

ROXUL INC. www.roxul.com Milton, Ontario Tel: 905-878-8474 Tel: 1-800-265-6878 Fax: 905-878-8077 Fax: 1-800-991-0110 Revised: August 7, 2007 Supersedes: June 1, 2007