

Technical Product Information

RockBoard 40

BOARD INSULATION 07210* BOARD INSULATION 07 21 13** ACOUSTIC BOARD INSULATION 09 81 13** PROCESS EQUIPMENT INSULATION 40 42 23**

General Product Information:

ROXUL® products are mineral wool fibre insulations made from basalt rock and slag. This combination results in a noncombustible product with a melting point of approximately 2150°F (1177°C), which gives it excellent fire resistance properties. ROXUL mineral wool is a water repellent yet vapour permeable material.

Description & Common Applications:

The RockBoard[™]40 product is a semi-rigid mineral wool insulation board that is non-combustible, water repellent, fire resistant and sound absorbent. This product is a general all purpose board with low thermal conductivity. This board can also be fabricated to different dimensions while still retaining fire, water and thermal properties.

Compliance and Performance:

ASTM C 612 Mineral Fiber Block and Board Thermal Insulation Type IVA, Complies

Fire Performance:

ASTM E 136 Behaviour of Materials at 750°C (1382°F) Non-Combustible
CAN4 S114 Test for Non-Combustibility Non-Combustible
ASTM E 84(UL 723) Surface Burning Characteristics Flame Spread = 5
Smoke Developed = 5

CAN/ULC S102 Surface Burning Characteristics Flame Spread = 5 Smoke Developed = 10

Maximum Service Temperature:

ASTM C 411 Hot Surface Performance In Compliance with

ASTM C612 @ 1200°F(650°C)

Dimensional Stability:

ASTM C 356 Linear Shrinkage 0.47% @ 1200°F (650°C)

Moisture Resistance:

ASTM C 1104 Moisture Sorption 0.03%

Fungi Resistance

ASTM C1338 Determination of Fungi Resistance Passed

Thermal Resistance:

ASTM C 518 (C 177) R-value/inch @ 75°F 4.1 hr.ft².F/Btu***
RSI value/25.4 mm @ 24°C 0.72 m²K/W

Corrosive Resistance:

ASTM C 665 Corrosiveness to Steel


ASTM C 795 **** Stainless Steel Stress Corrosion Specification as per Test


Methods C871 and C692: U.S. Nuclear Regulatory Commission, Reg. Guide #1.36: U.S. Military Specifications MIL-I-24244 (all

versions including B and C)



Thermal Conductivity (k):





Acoustical Performance

ASTM C423 CO-EFFICIENTS AT FREQUENCIES							
Thickness	125 Hz	250 Hz	500 Hz	1000 Hz	2000 Hz	4000 Hz	NRC
1.0"	0.07	0.32	0.77	1.04	1.05	1.05	0.80
1.5"	0.18	0.48	0.96	1.09	1.05	1.05	0.90
2.0"	0.26	0.68	1.12	1.10	1.03	1.04	1.00
3.0"	0.63	0.95	1.14	1.01	1.03	1.04	1.05
4.0"	1.03	1.07	1.12	1.04	1.07	1.08	1.10

Compressive Strength:

ASTM C 165 at 10% 90 psf (4.3 kPa) at 25% 226 psf (10.8 kPa)

Density:

ASTM C 612-00 – Actual 4.0 lbs/ft³ 64 kg/m³

Dimensions:

24" (width) x 48" (length)

610 mm (width) x 1219 mm (length)

Thickness:

Product is available in 1" through 4" in half inch increments as well as a 5" offering

For additional sizes, please contact our customer service representatives.

Facing:

This product can be faced with reinforced foil facing. Please note that the facings will influence the product's service temperature range.

Key Application Qualifiers:

- Water repellent
- Durability
- Ease of application
- Fire resistance
- Excellent thermal resistance
- Low moisture sorption
- Non-corrosive
- Chemically inert
- CFC and HCFC free product and process
- Made from natural & recycled materials

Other ROXUL Products:

Please consult ROXUL for all your insulation needs. We have an extensive range of products for all applications from pipe insulation to commercial products to residential batts. ROXUL invites all inquiries and will act promptly to service all of your requirements.

Note:

As ROXUL Inc. has no control over installation design and workmanship, accessory materials or application conditions, ROXUL Inc. does not warranty the performance or results of any installation containing ROXUL Inc's. products. ROXUL Inc's. overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty is in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose.

ROXUL INC. www.roxul.com Milton, Ontario Tel: 905-878-8474 Tel: 1-800-265-6878

Fax: 1-800-991-0110 Revised: August 7, 2007 Supersedes: June 1, 2007

Fax: 905-878-8077

^{**** &}quot;Provisions for lot testing may be required, consult manufacturer."